

WB-35/SOX

Cat.-no.: 2125

No clean, water based flux, VOC-free, di-carboxylic acids, resin-free, halogen-free (WEEE/RoHS conformant)
Type 2.1.3.1 // ORLO acc. ISO 9454 // DIN EN 61 190-1-1



Customer added value

- Non-flammable (no legal restrictions for transport, storage and handling)
- Very good soldering properties (capillarity, wetting)
- Broad process window (high thermal stability, good activity over a long interval)
- Very good residue behaviour (optically very clean, high SIR)

Technical data:

Appearance	colorless, clear
Solids content wt%	3.5
Density 20°C-g/cm ³	1.00 - 1.02
Acid number mg KOH/g	28 - 32
Activators/resin	di-carboxylic acids
Solvents	water
Flash point °C	non-flammable
Durability (months)	12

Image may differ from the original.

Application

- ▶ Wave soldering (spray fluxing)

Standard packaging units



20l